

weber tylon® WB11

24 hr adhesive for all ceramic tiles



DESCRIPTION

weber tylon® WB11 Ceramic is a grey general purpose cement-based adhesive for fixing light weight or soft baked ceramic wall and floor tiles in interior and external installations. This adhesive has an 8-hour pot life and designed for easy application.



Easy to apply



Easy to apply



Trowel Application

USES

Suitable for fixing lightweight or soft baked glazed ceramic wall & floor tiles to cement plaster, screeds, and concrete surfaces.

- Indoor and outdoor use
- Suitable for wall and floors
- 8 hr pot life

SUITABLE SURFACES

weber tylon® WB11 Ceramic is suitable to use on surfaces like:

- Cement-based plaster
- Cement screeds
- Concrete surfaces

TECHNICAL DATA

Initial setting time	approximately 12 hours
Final setting time	approximately 24 hours
Correction time	approximately 20 minutes
Open time	approximately 20 minutes
Pot life	approximately 8 hour
Grouting time	approximately 24 hour
Water demand	approximately 5 litres per 20 kg
Temperature resistance	70 °C
Application temperatures	<p>Note: all the data given was obtained at a temperature of 23 °C and 50% relative humidity. weber tylon® WB11 Ceramic is designed to meet the following SANS 52004 related performance values.</p> <p>Do not apply in temperatures below 5 °C or above 30 °C</p>

SURFACE PREPARATION

The following minimum curing periods should be observed before tiling commences:

- New concrete floors: 28 days
- New screeds: 28 days
- New brick walls: 28 days
- New cement plaster: 28 days

It is recommended that the substrate is clean, dry, and sound and free from dust, grease or any contamination that could impair bonding.

The walls or floors to be tiled must be wood-floated and not steel-troweled or power-floated. Repair any damaged areas and remove loose or peeling layers before proceeding with tiling. Organic growth must be removed and the spores killed using household bleach. PVA paint and gypsum plaster must be chipped to expose 80% of the substrate. Enamel paint and bitumen should be scraped and chipped to expose 80% of the substrate.

Do not use a solvent or heat to remove bitumen from the surface. Existing tiles must be thoroughly cleaned using a suitable cleaner.

Weber Tylon® WB11

Rinse well with cold water. Smooth-, off-form-, shutter- or power floated cement surfaces should be acid washed to remove laitance. Rinse well with cold water.

Once the surface preparation has been completed on the above problem surfaces, the area must be primed using a mix of 2 volumes of **weber tylon® Plaskey** and 1 volume of **weber tylon® Key-it**. Apply to a thickness of approximately 2 mm using a block brush. Leave to dry for 24 hours.

MIXING

- Combine a 20 kg bag of **weber tylon® WB11 Ceramic** with approximately 5 litres of clean water and mix to a creamy paste
- In wet or permanently wet conditions, replace the water in the mix with **weber tylon® Bond-it**
- Allow the mixture to mature for 5 minutes and re-mix thoroughly. The consistency can be adjusted by adding more water
- Do not add too much water or attempt to extend the working time by adding more water as this will cause the adhesive to be weak with a tendency to crumble
- Do not mix more adhesive than can be applied within 1 hour

APPLICATION

Spread adhesive using a notched trowel to a minimum bedded thickness of 3 mm on walls and 5 mm on floors. Heavily lugged, grooved or dove-tailed tiles must be buttered to fill any voids with adhesive before placing into wet adhesive. Press tiles firmly into wet adhesive with a twisting action. Use a rubber mallet to bed large or heavy tiles. Occasionally lift a tile to check that full contact is being made between the tile and the adhesive. Do not butt joint tiles.

Clean excess adhesive off the surface once tiles are firmly set using a damp sponge. Once the adhesive has hardened, only mechanical removal is possible. Minimum grouting joints for walls is 2 mm and 3 mm for floors. Adhesive must be allowed to dry for 6 hours before grouting commences.

GROUTING

Ensure that the joints are free from tile adhesive and any other foreign matter. Allow 24 hours before grouting with **weber tylon® Tile Grout**. In wet or permanently wet conditions, replace the water in the mix with **weber tylon® Bond-it**.

COVERAGE

Depending of the nature and evenness of the surface and method of application, approximately 6 m² per 20 kg bag when applied using a 6 mm notched trowel (wall tiling) and 4 m² per 20 kg bag when applied using a 10 mm notched trowel, (floor tiling) i.e. based on a level/even floor.

PACKAGING

weber tylon® WB11 Ceramic is supplied in 20 kg bags.

STORAGE AND SHELF LIFE

When stored, unopened in a dry place at temperatures above 5 °C, shelf life is 12 months from date of manufacture.

SAFETY INSTRUCTIONS

Contains cement, which is alkaline when wet and can cause skin irritation. Use eye protection and gloves and avoid prolonged skin contact. Avoid inhalation of dust. Wash skin contamination away with warm soapy water. Remove splashes to the eyes by prolonged irrigation and consult a doctor. Do not ingest.

GUARANTEE

We agree that **weber** products meet the product specifications and will be free from any defect. Any guarantee with regard to the performance of **weber** products will be subject to its professional and practical application of **weber** products in accordance with our instructions and specifications. However, we have no influence over specific site conditions and therefore, if in doubt, the user should first carry out sufficient tests to ensure that the product is suitable. In special cases, obtain advice. Should our product prove defective, we undertake to replace any defective material. This guarantee will fall away in the event of **weber** products being contaminated by the addition of sand, cement or substance other than recommended by us.

TECHNICAL SERVICES

Weber has a team of experienced advisors available to provide technical support. Technical helpline: 08600 WEBER (93237) or visit www.za.weber.